

Specification Sheet

Product Name: **PEEK pure resin granules**
Specifications & Purity: Standard liquidity for continuous extrusion
SKU # **P580717**

Parameter	Limit Values
Appearance(P580717)	White to Beige granule
Infrared spectrum	Conforms to Structure
Tensile strength	≥90 (MPa)
Tensile Elongation	≥15 (%)
Impact Strength	≥5 (KJ/M2)
Flexural Strength	≥125 (MPa)
Melt index	8-12 (g/10min)
Flexural Modulus	≥3.4 (GPa)
Specific gravity	1.28-1.32 (g/ml)