

Aladdin warrants, that at the time of the quality release or subsequent retest date this product conformed to the information contained in this publication. The current Specification sheet may be available at Aladdin-e.com. For further inquiries, please contact Technical Service. Purchaser must determine the suitability of the product for its particular use. See reverse side of invoice or packing slip for additional terms and conditions of sale.

## **Specification Sheet**

Product Name: D.E.N.™ 438 Epoxy Novolac Resin

Specifications & Purity: Epoxy equivalent: 176-181g/eq, viscosity (51.7 °C): 31000-40000 cps

SKU# **P477976** 

Parameter Limit Values

Infrared spectrum Conforms to Structure
Appearance(P477976) Colorless Solid or Liquid
Viscosity(51.7°C) 31000-40000 (cps)

Epoxide Equivalent Weight 176-181 (g/Eq)
Hydrolysable Chlorine 0-1200 (ppm)
epichlorohydrin 0-5 (ppm)

Volatiles 0-0.3 (%)

Aladdin warrants, that at the time of the quality release or subsequent retest date this product conformed to the information contained in this publication. The current Specification sheet may be available at Aladdin-e.com. For further inquiries, please contact Technical Service. Purchaser must determine the suitability of the product for its particular use. See reverse side of invoice or packing slip for additional terms and conditions of sale.

Phone: +86 400 620 6333 Email: Sale@aladdin-e.com Web: https://www.aladdin-e.com